

CONTI SECUR BFA - instructions for rubber-rubber bonding



CONTI SECUR BFA is a two component adhesive system for cold bonding applications. It is designed specifically for cold splicing and cold repair of conveyor belts, but also for all areas of wear and corrosion protection. Continual high adhesion strength is achieved, even for dynamic demands.

Storage:	At room temperature. If the adhesive is stored at temperatures of 6°C (43°F) or colder, the chloroprene rubber compound crystallizes. This leads to a change in viscosity. The adhesive becomes tacky. In this condition, because an optimum adhesion cannot be achieved, the solution cannot be used. However, after warming up the adhesive to room temperature, the product can be used again as described below.
Use:	Above 10°C (50°F).
Shelf life:	At least 24 months after date of production.
Heat resistance:	≤ 50°C (122°F), for short-term up to max. 90°C (194°F).

› Preparation of CONTI SECUR BFA

1. Mix CONTI SECUR BFA with Activator RE in a mixing ratio of 20:1.



2. Obtain flat bottom, square edged rectangular stirrer made from wood or plastic (Note: not metal, not round). Insert stirrer squarely, ensuring flat edge is pressed firmly against the bottom of the can and the stirrer is pushed into the corner of the can. While pressing down firmly, completely scrape the can's bottom once.
3. Lift spatula out and inspect. There will be a large buildup of solids. The buildup is a critical component of the adhesive.



Note: Do not discard!
Do not scrape off on the edge of the can!

4. Reinsert the stirrer into the can. Repeat scraping the entire bottom of the can two more times and stir using a fast up-down corkscrew motion until all solids have dissolved off the end of the stick. Product is now ready to use.
Note: Stir again before each use.

› Preparation of the material

5. The surfaces of the materials that are to be joined should preferably be at room temperature. If the temperature is too low, we recommend warming up the materials.
6. Etch the rubber surface of the base material with the aid of a grinder. Remove all dust.



Note: Use a grinder grit size 16-24.
Minimum speed: 600 rpm
Maximum speed: 1800 rpm

› Preparation of the material (continued)

7. a) Clean the contact layer with solvent (CONTI Cleaning Solution).



- b) Buff the surface of the rubber using a grinder. Remove all dust.



Note: Use a grinder grit size 36-60.
Minimum speed: 600 rpm
Maximum speed: 1800 rpm

8. Cut the rubber to size

› Bonding

9. Apply the first thin coat of CONTI SECUR BFA to the rubber surfaces.



Drying time: At least 30 minutes at room temperature. 60 minutes are suggested for optimal adhesion. Check with the back of the hand.

Back of the hand test: At the optimum drying time the adhesive is tacky but does not transfer to the back of your hand. Rubber coated cloth gloves work best.

Note: Use a brush with short bristles.

Caution: At room temperature the maximum drying time should not exceed 12 hours.

Note: One coat of CONTI SECUR BFA is usually sufficient. In this event, please skip this step 9 for the contact layer and prepare the contact layer together with the second coat of the base material (step 10).

10. Apply the second thin coat of CONTI SECUR BFA to rubber surfaces.
Drying time: Maximum of 10 minutes at room temperature. Check with the back of the hand.

Note: A third application of CONTI SECUR BFA may be required if the surface of the rubber is particularly rough. In this event, repeat the instructions from step 9 and let the material dry again for at least 30 minutes at room temperature. 60 minutes are suggested for optimal adhesion. Thereafter continue with this step 10.

11. With a hand-held roller or a dead-blow hammer, press from the center to the edges. The required strength of contact pressure depends on the properties of the surfaces.



Note: Brief contact pressure is sufficient.

12. In order to even the surface of the patch, etch with an angle grinder.



Note: Use a grinder grit size 36-60.
Minimum speed: 600 rpm
Maximum speed: 1800 rpm

13. The above prepared material can be used after 6 hours without load, and 12 hours with load. Optimum adhesion strength is attained after 24 hours.

